

# PATENT ABSTRACTS OF JAPAN

(11)Publication number : 06-095150

(43)Date of publication of application : 08.04.1994

(51)Int.Cl.

G02F 1/136

G02F 1/133

G02F 1/1343

H01L 29/784

(21)Application number : 04-244521

(71)Applicant : HITACHI LTD

(22)Date of filing : 14.09.1992


(72)Inventor : YAMAMOTO HIDEAKI  
SHIROHASHI KAZUO  
KASE KENICHI

## (54) THIN-FILM TRANSISTOR SUBSTRATE AND LIQUID CRYSTAL DISPLAY DEVICE AND ITS PRODUCTION

### (57)Abstract:

**PURPOSE:** To eliminate the connection defects of ITO films and Al gate wirings and to shorten the stages by constituting terminals of indium oxide films (ITO films) and electrically connecting these ITO films and the Al gate wirings with Cr films.

**CONSTITUTION:** The ITO film 17 is formed by sputtering and vapor deposition on a thin-film transistor substrate 10 and in succession, the Cr film 11 is formed by sputtering thereon. Patterning of gate terminals G1, G2 and pixel electrodes 17 is executed by photoetching. The sectional shapes are trimmed by etching the Cr film 11 and etching the ITO film 1y, then etching the Cr film 11 again at this time. The Al-Ta 12 is then deposited by evaporation and is photoetched, by which the patterns of gate wirings G1', G2' of Al (Ta), additive capacitors Cadd and gate electrodes are formed. The stages are shortened by simultaneously executing the formation of the terminals and the formation of the pixel electrodes in such a manner.



### LEGAL STATUS

[Date of request for examination] 17.02.1999

[Date of sending the examiner's decision of rejection] 23.01.2001

[Kind of final disposal of application other than the examiner's decision of rejection or application]

converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office

**\* NOTICES \***

Japan Patent Office is not responsible for any damages caused by the use of this translation.

1. This document has been translated by computer. So the translation may not reflect the original precisely.

2. \*\*\*\* shows the word which can not be translated.

3. In the drawings, any words are not translated.

---

**CLAIMS**

---

**[Claim(s)]**

[Claim 1] Two or more gate terminals formed on the insulating substrate, and two or more gate wiring which extends in it, In the thin film transistor substrate which comes to arrange a thin film transistor at the intersection of two or more signal wiring arranged by intersecting this, and said gate wiring and signal wiring The thin film transistor substrate characterized by for said gate terminal consisting of only transperence electric conduction film, and connecting it with said gate wiring electrically through Cr film in the point.

[Claim 2] The thin film transistor substrate according to claim 1 characterized by said gate wiring consisting of an aluminum alloy.

[Claim 3] The thin film transistor substrate according to claim 1, or 2 with which said aluminum alloy is characterized by the thing of Ta and Ti included for any they are at least.

[Claim 4] A thin film transistor substrate given in any of claims 1, 2, and 3 characterized by the gate dielectric film of said thin film transistor containing the anodized film of said aluminum alloy they are.

[Claim 5] The above-mentioned transperence electric conduction film is a thin film transistor substrate given in any of claims 1, 2, 3, and 4 characterized by being the oxidization in JUUMU film they are.

[Claim 6] The manufacture approach of a thin film transistor substrate given in whether any of claims 1, 2, 3, and 4 characterized by to have the process which performs said anodic oxidation by leading a current to the terminal with which the formation process of said gate terminal and a pixel electrode consists of a process which patternizes by the two-layer structure film of the transperence electric-conduction film and Cr film formed on it, removes the account Cr film of Gokami, and is used only as the transperence electric-conduction film, and said transperence electric conduction they are.

[Claim 7] The liquid crystal display panel characterized by having a thin film transistor substrate given in any [ claim 1 thru/or ] of 4 they are.

[Claim 8] The liquid crystal display characterized by having the video-signal drive circuit for giving a video signal to a liquid crystal display panel according to claim 7 and this liquid crystal display panel, a scanning circuit for giving a scan signal, and a control circuit for giving the information for liquid crystal display panels to this video-signal drive circuit and this scanning circuit.

[Claim 9] The above-mentioned transperence electric conduction film is the manufacture approach of the thin film transistor substrate according to claim 6 characterized by being the oxidization in JUUMU film.

---

[Translation done.]

**\* NOTICES \***

Japan Patent Office is not responsible for any damages caused by the use of this translation.

1. This document has been translated by computer. So the translation may not reflect the original precisely.

2. \*\*\*\* shows the word which can not be translated.

3. In the drawings, any words are not translated.

---

**DETAILED DESCRIPTION**

---

[Detailed Description of the Invention]

[0001]

[Industrial Application] This invention relates to the TFT substrate and liquid crystal display of a active-matrix drive mold which used the thin film transistor (it omits Following TFT).

[0002]

[Description of the Prior Art] The example of the TFT substrate which made 2Oaluminum3 film which anodizes this and is obtained the one section of gate dielectric film by setting gate wiring and a gate electrode to aluminum is explained using drawing 2 using amorphous silicon (it abbreviates to a-Si hereafter) TFT. Drawing 2 (a), (b), and (c) show the representative circuit schematic of a TFT substrate, a top view, and a sectional view respectively. As for a gate terminal, G1', and G2', as for G1 and G2, addition capacity and 17b show the common electrode with which TFT and LC are prepared in liquid crystal and Cadd is prepared [ gate wiring, and D1 and D2 ] for a drain terminal, and T11 and T12 in a color filter substrate side. In 10, a substrate and 11 aluminum and A for Cr of a gate terminal, and 12 Moreover, the connection part of Cr of a gate terminal, and aluminum of gate wiring, 13 — aluminum2O — 3 and 14 — SiN and 17 — an ITO transparent electrode (pixel electrode) — It is amorphous silicon (it abbreviates to a-Si (n+) hereafter) with which 15 doped non dope a-Si (i), and 16 doped Lynn, signal wiring and 18' are source electrodes, and 18 has connected TFT and a pixel electrode. Among drawing 2, a boundary line I1 shows the boundary of the field to anodize and the field which is not so, and anodizes the field on the right of a boundary line I1. PAD is a terminal for supplying a current required for anodic oxidation, L is a bus line for making common connection of all the gate terminals, and a boundary line I2 shows the part to cut after TFT substrate completion. Such a technique is indicated by JP,3-232274,A.

[0003] Thus, the cascade screen of Cr and a transparent electrode (it omits an in JUUMU oxide film and Following ITO) was conventionally used for the terminal area of a TFT substrate. Moreover, when aluminum metal was used for a gate electrode or gate wiring, as an ingredient, pure aluminum and aluminum which added Pd, Si, etc. as an impurity were used.

[0004] In a TFT substrate, the reason [ terminal area ] using the cascade screen of Cr and ITO is explained. It connects with the external circuit for driving in a terminal area, and a TFT substrate is used. For this reason, a terminal area is exposed to atmospheric air. Therefore, it is necessary to be the ingredient which has fear which the open circuit by the corrosion by moisture, the poor contact by oxidation, etc. produce, and does not have such a thing. At such a point, the combination of Cr and ITO is good and is used abundantly. On the other hand, aluminum was considered to be unsuitable by the terminal area that it is easy to deteriorate.

[0005]

[Problem(s) to be Solved by the Invention] Cr film is required for the above-mentioned conventional technique only because of a terminal area, and the process for carrying out the formation patternizing of this is required for it, and it had a problem in respect of cost or a yield.

[0006] The 1st purpose of this invention is by making this Cr film unnecessary to offer low cost and the TFT substrate of a high yield. The 2nd purpose of this invention is to offer the liquid crystal display panel which used this TFT substrate. The 3rd purpose of this invention is to offer the liquid crystal

display which used the above-mentioned liquid crystal display panel.

[0007]

[Means for Solving the Problem] Two or more gate terminals with which the 1st purpose of the above was formed on (1) insulation substrate, and two or more gate wiring which extends in it, In the thin film transistor substrate which comes to arrange a thin film transistor at the intersection of two or more signal wiring arranged by intersecting this, and said gate wiring and signal wiring The thin film transistor substrate characterized by for said gate terminal consisting of only oxidization in JUUMU film, and connecting it with said gate wiring electrically through Cr film in the point, (2) The thin film transistor substrate given in (1) characterized by said gate wiring consisting of an aluminum alloy, (3) The thin film transistor substrate given in (1) and (2) with which said aluminum alloy is characterized by the thing of Ta and Ti included for any they are at least, (4) A thin film transistor substrate given in (1) characterized by the gate dielectric film of said thin film transistor containing the anodized film of said aluminum alloy, (2), and (3) can attain. (5) It can manufacture by the approach characterized by having the process which the formation process of said gate terminal and a pixel electrode patternizes by the two-layer structure film of the oxidization in JUUMU film and Cr film formed on it, removes the account Cr film of Gokami, and uses only as the oxidization in JUUMU film. The liquid crystal display panel characterized by having a thin film transistor substrate given in (1), (2), (3), and (4) can attain the 2nd purpose of the above. The liquid crystal display characterized by having the video-signal drive circuit for giving a video signal to said liquid crystal display panel and this liquid crystal display panel, a scanning circuit for giving a scan signal, and a control circuit for giving the information for liquid crystal display panels to this video-signal drive circuit and this scanning circuit can attain the 3rd purpose of the above.

[0008] In this invention, a terminal is constituted from ITO and aluminum gate wiring is further connected electrically through Cr film by the point of ITO. Shortening of a process is attained by performing this terminal formation to pixel electrode formation and coincidence. In this case, the ingredient (it is hereafter described as aluminum-Ta, aluminum-Ti, and aluminum-Ta-Ti) which added Ta and Ti as an impurity from corrosion resistance as an aluminum ingredient to be used is applied. As concentration to add, 0.5 atoms % to 2.5 atom % is desirable. This reason is because the good oxide film on anode aluminum  $2O_3$  is obtained with this ingredient sufficient [ thermal resistance ].

[0009]

[Function] The above-mentioned technique has the next operation.

[0010] A gate terminal is used for gate wiring, connecting electrically. When a gate terminal is set to ITO and gate wiring is set to aluminum, cautions as shown below are required.

[0011] (1) It is that  $2O_{aluminum}3$  film which is an insulator layer is made in between, and aluminum and ITO of a substrate become a poor contact by the interface reaction of ITO and aluminum for this reason, when the laminating of the ITO is carried out on aluminum. This example is shown in drawing 3 . Properties C2, C3, and C4 show three examples of the electrical-potential-difference dependency of a current which flow aluminum and ITO between laminating *Perilla frutescens* (L.) Britton var. *crispa* (Thunb.) Decne. On the other hand, C1 shows the example which contacted Cr and ITO. Thus, compared with Cr/ITO, contact resistance is high, variation is also large, and aluminum and ITO are problems. Therefore, Cr film needed to be intervened when ITO and aluminum were connected.

[0012] (2) In the TFT substrate of this invention, there is a process which anodizes aluminum of the gate and is used as  $2O_{aluminum}3$  film. For performing this anodic oxidation, common connection of all the gate wiring is made, and an electrical potential difference is impressed. With what this common connection is made poses a problem. ITO of the gate was used in this invention.

[0013] (3) As much as possible few masks required for a TFT process for photoetching processes are wanted for there to be. In this invention, the process which a gate terminal and a pixel electrode can form in coincidence is offered. This is reducing the number of masks by one sheet conventionally.

[0014] It can anodize with an ITO terminal with this technique, and TFT with which there are few photo masks and it can moreover be managed can be offered so that clearly from the above explanation. Thereby, low-cost-izing of a TFT substrate and the improvement in a yield were realizable.

[0015]

[Example] Hereafter, this invention is explained to a detail using an example.

[0016] Drawing 1 (a) is the top view of the TFT substrate of one example of this invention, and (b) is the sectional view. Drawing 4 is the explanatory view of each part for rounding description. It has expressed with the sign with the equal part same identically to drawing 2. First, the manufacture approach of this substrate of TFT is described. The ITO film (17) is formed by 1400Å sputter vacuum evaporation on a substrate 10. Cr (11) is continuously formed by 1000Å sputter on it. The pattern of gate terminals G1 and G2 and a pixel electrode (17) is formed by photoetching. At this time, Cr film and the ITO film are continuously performed to coincidence. Sequence etches Cr, etches ITO, etches Cr once again, and prepares a cross-section configuration (refer to drawing 4 (a)). aluminum-Ta (addition 1.5 atom [ of Ta ] %) — 12 — about — 3000 — Å — thickness — sputtering — vapor-depositing — photoetching — aluminum — (— Ta —) — the gate — wiring — G — one — ' — G — two — ' — addition — capacity — Cadd — the gate — an electrode — a pattern — forming. Cr film is etched by using this aluminum (Ta) pattern as a mask. Cr of the pixel section and Cr of a part of terminal area are removed at this process. SURAITO etching of aluminum (Ta) is performed succeeding and a cross-section configuration is prepared. This etching removes that the end face of aluminum (Ta) has jutted out from the end face of Cr, and it is performed in order to lose the so-called overhang. then, the part (on the right of the boundary line l1 in drawing) to anodize and formation — it covers with a photoresist except for PAD. A gate circuit pattern and a photoresist pattern are made to intersect perpendicularly at this time. It anodizes in this condition. the anodic oxidation approach — formation — Pad PAD — the outside from an oil level — coming out — making — formation — liquid — dipping — formation — Pad PAD — a maximum of 72 — it carries out by impressing the direct current voltage of V to 144V. The pressure up of the approach of impression is gradually carried out from 0V so that it may become constant current 0.5 – 5 mA/cm<sup>2</sup>. Since a high current flows when a high electrical potential difference is impressed from the beginning, aluminum line melts and a gate line is disconnected. formation — what diluted with ethylene glycol liquid to 1:9 the solution which adjusted the tartaric acid to PH 7\*\*0.5 from ammonia 3% as liquid is used. When currents are 0.5 mA/cm<sup>2</sup>, formation voltage is set to 144V in about 10 minutes. The thickness of aluminum 2O3 (refer to 13 and drawing 4 (b) of drawing 1 (b)) formed at this time is 2000Å. This aluminum 2O3 is used as a dielectric of gate dielectric film and addition capacity. In addition, it is desirable to hold in the condition as it is for [ several minutes – ] several 10 minutes after being set to 144V and coming to perform constant-voltage oxidation. This is important, when obtaining 2Oaluminum3 uniform film.

[0017] It returns and explains to drawing 1 again. After removing a photoresist, 2000Å of SiN(s)14 is formed in the whole surface by the plasma-CVD method. The gas which uses SiH<sub>4</sub> and NH<sub>3</sub> as a main component as ingredient gas is used. 300Å (n+) of a-Si16 which moreover doped 2000Å and Lynn for a-Si (i)15 2.5% is deposited. At this time, it may be 300 degrees C as substrate temperature. As ingredient gas, a-Si uses the mixed gas of SiH<sub>4</sub> and PH<sub>3</sub> for a-Si (n+) for the gas which uses SiH<sub>4</sub> as a main component. Then, a-Si is patternized and it is made the shape of an array. The dry cleaning dirty method by SF<sub>6</sub> gas is used for etching of the plasma film. It is required to remove SiN so that the ITO film of ITO near a terminal and a pixel electrode may be exposed like drawing 4 (c) at this time. Cr/aluminum-Ta the signal wiring 18 which besides serves as the drain electrode of TFT, and for source electrodes (concentration 1.5 atom [ of Ta ] %) is formed and patternized in sputtering in thickness of 1000Å and 4000Å, respectively. At this time, it becomes like drawing 4 (d). Dry etching of a-Si (n+)16 is carried out by using a drain electrode as a mask after this. the last — as a protective coat — SiN — 1 micrometer — forming — SiN on a terminal area — removing — the back and formation — between a bus line L and gate terminals G1 and G2 is cut mechanically, and a TFT substrate is completed (refer to drawing 4 (e)).

[0018] Although drawing 1 showed the case where it had arranged so that each pixel may make a train, half-pitch gap \*\*\*\*\* is sufficient. Moreover, even when there is no addition capacity Cadd, of course, it can completely manufacture similarly. Although the alloy which added Ta was used for aluminum as an

aluminum ingredient here, the alloy which added Ti, and Ta and Ti to coincidence is sufficient. In this case, below 1.5 atom % of the amount to add is desirable from the point of resistance or an etch residue. [0019] Next, the translucency substrate with a counterelectrode and blue, red, and a green color filter array and the TFT substrate manufactured by the above were stuck and set using the spacer with a thickness of 7.3 micrometers, liquid crystal was closed in between, and the liquid crystal display panel was completed. The structure is explained briefly below.

[0020] The whole cross-section structure of an electrochromatic display display panel is shown in drawing 5. On the basis of liquid crystal LC, the TFT substrate in which TFT etc. was formed on the transparence glass substrate 10 is arranged by the lower part, and transparence glass substrate 10b by which the color filter FIL, the black matrix BM for protection from light, etc. were formed in the upper part is arranged.

[0021] The central part of drawing 5 shows the cross section of a 1-pixel part, left-hand side shows the cross section of a part where an external leader line exists by part for the left-hand side edge of the transparence glass substrates 10 and 10b, and right-hand side shows the cross section of the part in which an external leader line does not exist at a transparence glass substrate and the right-hand side edge of 10b. Sealant SL shown in each of the left-hand side of drawing 5 and right-hand side is constituted so that liquid crystal LC may be closed, and it is formed along the whole edge perimeter of the transparence glass substrates 10 and 10b except liquid crystal enclosure opening (not shown). Sealant SL is formed with the epoxy resin.

[0022] Common transparence pixel electrode 17b by the side of said up transparence glass substrate 10b is connected to external leader line 17' formed in the lower transparence glass substrate 10 side of the silver paste material SIL in at least one place. This external leader line is formed by the same production process as each of the gate electrode mentioned above, a source electrode, and a drain electrode.

[0023] Each layer of SiN14 which are the orientation film ORI1 and ORI2, a transparent electrode 17, common transparence pixel electrode 17b, protective coats 20 and 20b, and an insulator layer is formed inside sealant SL. Polarizing plates POL1 and POL2 are formed in the front face of each outside of the lower transparence glass substrate 10 and up transparence glass substrate 10b.

[0024] Liquid crystal LC is enclosed among the lower orientation film ORI1 and ORI2 which sets up the sense of a liquid crystal molecule, and the seal is carried out by sealant SL.

[0025] The lower orientation film ORI1 is formed in the upper part of the protective coat 20 by the side of the lower transparence glass substrate 10.

[0026] A light-shielding film BM, a color filter FIL, protective coat 20b, common transparence pixel electrode 17b, and the up orientation film ORI2 carry out a laminating to the front face inside up transparence glass substrate 10b (liquid crystal side) one by one, and are prepared in it.

[0027] One example of a liquid crystal display is shown in drawing 6. This equipment has the video-signal drive circuit 83 for giving a video signal to the liquid crystal display panel 81 and this liquid crystal display panel, the scanning circuit 84 for giving a scan signal to this liquid crystal display panel, and the control circuit 82 for giving TFT information to this video-signal drive circuit and a scanning circuit. A control circuit 82 includes a power circuit, the circuit which changes the information from a host processor into TFT information. When included in this equipment, using respectively the liquid crystal display panel obtained in said example, the image high quality [ all ] was obtained.

[0028]

[Effect of the Invention] By this invention, the production process of a TFT substrate could be shortened 12%, the yield could be improved further about 5%, and cost reduction was able to be planned.

**\* NOTICES \***

Japan Patent Office is not responsible for any damages caused by the use of this translation.

1.This document has been translated by computer. So the translation may not reflect the original precisely.

2.\*\*\*\* shows the word which can not be translated.

3.In the drawings, any words are not translated.

---

**DESCRIPTION OF DRAWINGS**

---

**[Brief Description of the Drawings]**

[Drawing 1] Drawing showing one example of this invention.

[Drawing 2] The explanatory view of the conventional technique.

[Drawing 3] Drawing showing the contact nature of aluminum and ITO.

[Drawing 4] Drawing for explaining the detail of each part of this invention.

[Drawing 5] Drawing showing the example of the liquid crystal display panel using the TFT substrate of this invention.

[Drawing 6] Drawing showing the example of the liquid crystal display using the TFT substrate of this invention.

**[Description of Notations]**

10 10b ... A substrate, 11 ... Cr, 12 ... aluminum-Ta alloy ingredient, 13 ... aluminum<sub>2</sub>O — 3 and 14 ... SiN and 15 ... a-Si (i) — 16 ... a-Si (n+), 17 ... A transparent electrode, 17b ... Common transporence pixel electrode, 18 ... Signal wiring, 18' ... 20 A source electrode, 20b ... Protective coat, 81 ... A liquid crystal display panel, 82 ... A control circuit, 83 ... Video-signal drive circuit, 84 ... A scanning circuit, G1, G2 ... A gate terminal, G1', G2' ... Gate wiring, D1 and D2 ... a drain terminal and L ... formation — a bus line and I2 ... a cutting plane line — I1 ... formation — a boundary line and Cadd ... addition capacity and PAD ... formation — a terminal, and ORI1 and ORI2 ... the orientation film, and POL1 and POL2 ... a polarizing plate and FIL ... a color filter and LC ... liquid crystal and BM ... a black matrix and BL ... a back light.

---

[Translation done.]



(19)日本国特許庁(JP)

(12) 公開特許公報(A)

(11)特許出願公開番号

特開平6-95150

(43)公開日 平成6年(1994)4月8日

(51)Int.Cl. <sup>5</sup>	識別記号	序内整理番号	FI	技術表示箇所
G 0 2 F	1/136	5 0 0	9018-2K	
	1/133	5 0 5	9226-2K	
	1/1343		9018-2K	
H 0 1 L	29/784			
		9056-4M	H 0 1 L 29/ 78	3 1 1 A
			審査請求 未請求 請求項の数 9(全 7 頁)	

(21)出願番号 特願平4-244521

(22)出願日 平成4年(1992)9月14日

(71)出願人 000005108

株式会社日立製作所

東京都千代田区神田駿河台四丁目6番地

(72)発明者 山本 英明

千葉県茂原市早野3300番地 株式会社日立  
製作所茂原工場内

(72)発明者 白橋 和男

千葉県茂原市早野3300番地 株式会社日立  
製作所茂原工場内

(72)発明者 加瀬 賢一

千葉県茂原市早野3300番地 株式会社日立  
製作所茂原工場内

(74)代理人 弁理士 小川 勝男


(54)【発明の名称】 薄膜トランジスタ基板及び液晶表示装置及びその製造方法

(57)【要約】


【目的】 信頼性が高く、製造が容易な薄膜トランジスタ基板の端子部を得ること。

【構成】 薄膜トランジスタ基板の端子部を透明導電膜17のみで構成し、ゲート配線12との電気的な接続を確保する為、クロム導電層11を介在させた。

図1 (a)



(b)



ゲート端子部 10

TFT部 画素部 付加容量部 10

10:基板  
11:Cr  
12:Al合金  
13:Al<sub>2</sub>O<sub>3</sub>  
14:SiN  
15:a-Si(i)  
16:a-Si(n<sup>+</sup>)  
17:透明電極  
18:信号配線  
18':ソース電極

20:保護膜  
G<sub>1</sub>, G<sub>2</sub>:ゲート端子  
G<sub>1</sub>, G<sub>2</sub>:ゲート配線  
D<sub>1</sub>, D<sub>2</sub>:ドレイン端子  
I<sub>1</sub>:陽極酸化境界  
I<sub>2</sub>:切断線  
PAD:電流供給端子  
L:バスライン  
B:接続部  
Cadd:付加容量

(2)

1

## 【特許請求の範囲】

【請求項1】絶縁性基板上に形成された複数本のゲート端子とそれに延在する複数本のゲート配線と、これと交差して配置された複数本の信号配線と、前記ゲート配線と信号配線との交点に薄膜トランジスタを配置してなる薄膜トランジスタ基板において、前記ゲート端子が、透明導電膜だけで構成され、且つ、その先端部においてCr膜を介して前記ゲート配線と電気的に接続されていることを特徴とする薄膜トランジスタ基板。

【請求項2】前記ゲート配線がAl合金からなることを特徴とする請求項1記載の薄膜トランジスタ基板。

【請求項3】前記Al合金がTa、Tiのすくなくとも何れかを含むことを特徴とする請求項1又は請求項2記載の薄膜トランジスタ基板。

【請求項4】前記薄膜トランジスタのゲート絶縁膜が前記Al合金の陽極酸化膜を含むことを特徴とする請求項1、2、3の何れかに記載の薄膜トランジスタ基板。

【請求項5】上記透明導電膜は酸化インジウム膜であることを特徴とする請求項1、2、3、4の何れかに記載の薄膜トランジスタ基板。

【請求項6】前記ゲート端子及び画素電極の形成工程が、透明導電膜とその上に形成されたCr膜の2層構造膜でパターン化を行いその後上記Cr膜を除去して透明導電膜のみにする工程と前記透明導電からなる端子に電流を通じることによって前記陽極酸化を行う工程とを有することを特徴とする請求項1、2、3、4の何れかに記載の薄膜トランジスタ基板の製造方法。

【請求項7】請求項1ないし4の何れかに記載の薄膜トランジスタ基板を有することを特徴とする液晶表示パネル。

【請求項8】請求項7記載の液晶表示パネルと、該液晶表示パネルに映像信号を与えるための映像信号駆動回路と、走査信号を与えるための走査回路と、該映像信号駆動回路及び該走査回路に液晶表示パネル用の情報を与えるための制御回路とを有することを特徴とする液晶表示装置。

【請求項9】上記透明導電膜は、酸化インジウム膜であることを特徴とする請求項6記載の薄膜トランジスタ基板の製造方法。

## 【発明の詳細な説明】

## 【0001】

【産業上の利用分野】本発明は薄膜トランジスタ（以下TFTと略す）を使用したアクティブマトリクス駆動型のTFT基板および液晶表示装置に関する。

## 【0002】

【従来の技術】非晶質シリコン（以下、a-Siと略す）TFTを用い、ゲート配線、ゲート電極をAlとして、これを陽極酸化して得られるAl<sub>2</sub>O<sub>3</sub>膜をゲート絶縁膜の1部としたTFT基板の例を図2を用いて説明する。図2（a）（b）（c）は各々TFT基板の等価回

2

路図、平面図、断面図を示す。G<sub>1</sub>、G<sub>2</sub>はゲート端子、G<sub>1</sub>'、G<sub>2</sub>'はゲート配線、D<sub>1</sub>、D<sub>2</sub>はドレイン端子、T<sub>11</sub>、T<sub>12</sub>はTFT、LCは液晶、Caddは付加容量、17bはカラーフィルタ基板側に設けられる共通電極を示す。また、10は基板、11はゲート端子のCr、12はAl、Aはゲート端子のCrとゲート配線のAlとの接続部分、13はAl<sub>2</sub>O<sub>3</sub>、14はSiN、17はITO透明電極（画素電極）、15はノンドープa-Si（i）、16はリンをドープした非晶質シリコン（以下、a-Si（n+）と略す）、18は信号配線、18'はソース電極でありTFTと画素電極とを接続している。図2中、境界線11は陽極酸化する領域とそうでない領域との境界を示すもので、境界線11より右の領域は陽極酸化する。PADは陽極酸化に必要な電流を供給するための端子であり、Lは全てのゲート端子を共通接続するためのバスラインであり、境界線12はTFT基板完成の後、切断する部分を示す。このような技術は、特開平3-232274号公報に開示されている。

【0003】このように従来、TFT基板の端子部にはCrと透明電極（インジウム酸化膜、以下ITOと略す）との積層膜が用いられていた。また、ゲート電極やゲート配線にAl金属を用いる場合、材料としては純Alや不純物としてPdやSiなどを添加したAlが用いられていた。

【0004】TFT基板において端子部をCrとITOとの積層膜を用いる理由を説明する。TFT基板は端子部において駆動するための外部回路と接続し使用される。このため端子部は大気にさらされる。したがって、水分による腐食での断線や、酸化による接触不良などが生じるおそれがあり、このようなことがない材料である必要がある。このような点でCrとITOとの組合せが良く、多用されている。一方、Alは変質しやすく端子部には不相当と考えられていた。

## 【0005】

【発明が解決しようとする課題】上記従来技術は端子部だけのためにCr膜が必要であり、これを形成パターン化するための工程が必要でありコストや歩留の点で問題があった。

【0006】本発明の第1の目的はこのCr膜を不要にすることによって、低コスト、高歩留のTFT基板を提供することにある。本発明の第2の目的は、このTFT基板を用いた液晶表示パネルを提供することにある。本発明の第3の目的は、上記の液晶表示パネルを用いた液晶表示装置を提供することにある。

## 【0007】

【課題を解決するための手段】上記第1の目的は、

（1）絶縁性基板上に形成された複数本のゲート端子とそれに延在する複数本のゲート配線と、これと交差して配置された複数本の信号配線と、前記ゲート配線と信号配線との交点に薄膜トランジスタを配置してなる薄膜ト

(3)

3

ランジスタ基板において、前記ゲート端子が、酸化インジウム膜だけで構成され、且つ、その先端部においてCr膜を介して前記ゲート配線と電氣的に接続されていることを特徴とする薄膜トランジスタ基板、(2)前記ゲート配線がAl合金からなることを特徴とする(1)記載の薄膜トランジスタ基板、(3)前記Al合金がTa、Tiのすくなくとも何れかを含むことを特徴とする

(1)(2)記載の薄膜トランジスタ基板、(4)前記薄膜トランジスタのゲート絶縁膜が前記Al合金の陽極酸化膜を含むことを特徴とする(1)(2)(3)記載の薄膜トランジスタ基板で達成でき、(5)前記ゲート端子及び画素電極の形成工程が、酸化インジウム膜とその上に形成されたCr膜の2層構造膜でパターン化を行いその後上記Cr膜を除去して酸化インジウム膜のみにする工程を有することを特徴とする方法で製造できる。上記第2の目的は(1)(2)(3)(4)記載の薄膜トランジスタ基板を有することを特徴とする液晶表示パネルにより達成できる。上記第3の目的は前記液晶表示パネルと、該液晶表示パネルに映像信号を与えるための映像信号駆動回路と、走査信号を与えるための走査回路と、該映像信号駆動回路及び該走査回路に液晶表示パネル用の情報を与えるための制御回路とを有することを特徴とする液晶表示装置により達成できる。

【0008】本発明においては、端子をITOで構成し、さらにITOの先端部でCr膜を介してAlゲート配線とを電氣的に接続する。この端子形成を画素電極形成と同時にすることによって、工程の短縮化が可能となる。この場合使用するAl材料としては耐腐食性から不純物としてTa、Tiを添加した材料(以下、Al-Ta、Al-Ti、Al-Ta-Tiと記す)を適用する。添加する濃度としては0.5原子%から2.5原子%が望ましい。この理由は本材料が耐熱性が良く、また、良質の陽極酸化膜Al<sub>2</sub>O<sub>3</sub>が得られるためである。

【0009】

【作用】上記技術は次の作用がある。

【0010】ゲート端子はゲート配線と電氣的に接続して使用される。ゲート端子をITOとしゲート配線をAlとした場合次に示すような注意が必要である。

【0011】(1)それはAlの上にITOを積層した場合、ITOとAlとの界面反応により、間に絶縁膜であるAl<sub>2</sub>O<sub>3</sub>膜ができ、このため下地のAlとITOとが接触不良になることである。図3にこの例を示す。特性C<sub>2</sub>、C<sub>3</sub>、C<sub>4</sub>はAlとITOとを積層しその間に流れる電流の電圧依存性の3例を示すものである。一方、C<sub>1</sub>はCrとITOとを接触した例を示す。このようにCr/ITOに比べて、AlとITOとは接触抵抗が高くバラツキも大きく問題である。したがって、ITOとAlとを接続する場合はCr膜を介在する必要がある。

【0012】(2)本発明のTFT基板ではゲートのA

4

lを陽極酸化してAl<sub>2</sub>O<sub>3</sub>膜にする工程がある。この陽極酸化を行うには全てのゲート配線を共通接続して電圧を印加する。この共通接続を何で行うかが問題となる。本発明ではゲートのITOを利用した。

【0013】(3)TFT工程に必要なホトエッチングプロセス用のマスク数はできるだけ少ないことが望まれる。本発明ではゲート端子と画素電極とが同時に形成出来るようなプロセスを提供している。これにより、従来よりマスク数を1枚低減している。

【0014】以上の説明から明かなように、本技術によりITO端子で、陽極酸化が可能で、しかもホトマスク数が少なく済むTFTが提供できる。これによりTFT基板の低コスト化、歩留向上が実現できた。

【0015】

【実施例】以下、本発明を実施例を用いて詳細に説明する。

【0016】図1(a)は本発明の一実施例のTFT基板の平面図、(b)はその断面図である。図4は工程説明のための各部の説明図である。図2と同一又は均等部分は、同じ符号で表してある。まず、このTFTの基板の製造方法を述べる。基板10の上にITO膜(17)を1400Åスパッタ蒸着で形成する。連続してその上にCr(11)を1000Åスパッタにより形成する。ホトエッチングによりゲート端子G1、G2および画素電極(17)のパターンを形成する。この時Cr膜とITO膜とは連続して同時に行う。順序はCrをエッチングし、ITOをエッチングし、もう一度Crをエッチングして断面形状を整える(図4(a)参照)。Al-Ta(Taの添加量1.5原子%)12を約3000Åの厚みにスパッタリングにより蒸着し、ホトエッチングによりAl(Ta)のゲート配線G1'、G2'、付加容量Cadd、ゲート電極のパターンを形成する。このAl(Ta)パターンをマスクとしてCr膜をエッチングする。この工程で画素部のCrと端子部の一部のCrが除去される。引き続きAl(Ta)のスライトエッチングを行い断面形状を整える。このエッチングは、Al(Ta)の端面がCrの端面より張り出しているのを除去し、いわゆるオーバーハングをなくす為に行う。その後、陽極酸化する部分(図中境界線11より右)と化成PADとを除いてホトレジストで被覆する。この時、ゲート配線パターンとホトレジストパターンとは直交させる。この状態で陽極酸化を行う。陽極酸化方法は、化成パッドPADが液面から外に出るようにして化成液に浸し、化成パッドPADに最大72Vから144Vの直流電圧を印加して行う。印加の方法は定電流0.5~5mA/cm<sup>2</sup>になるように徐々に0Vから昇圧する。最初から高い電圧を印加した場合、大電流が流れるため、Al線が溶けゲート線が断線する。化成液としては3%酒石酸をアンモニアよりPH7±0.5に調整した溶液をエチレングリコール液で1:9に希釈したものをを用い

(4)

5

る。電流が $0.5\text{mA}/\text{cm}^2$ の場合、約10分間で化成電圧が144Vになる。この時形成された $\text{Al}_2\text{O}_3$  (図1(b)の13および図4(b)参照)の厚みは $2000\text{\AA}$ である。この $\text{Al}_2\text{O}_3$ はゲート絶縁膜及び付加容量の誘電体として利用する。なお、144Vになり定電圧酸化が行われるようになってから、数分〜数10分間そのままの状態に保持する事が望ましい。これは均一な $\text{Al}_2\text{O}_3$ 膜を得る上で大事なことである。

【0017】再び図1に戻って説明する。ホトレジストを除去した後、全面にプラズマCVD法により、 $\text{SiN}$  14を $2000\text{\AA}$ 形成する。材料ガスとしては $\text{SiH}_4$ 、 $\text{NH}_3$ を主たる成分とするガスを使用する。その上に、 $\text{a-Si(i)}15$ を $2000\text{\AA}$ 、リンを2.5%ドーピングした $\text{a-Si(n+)}16$ を $300\text{\AA}$ 堆積する。この時基板温度としては $300^\circ\text{C}$ とする。材料ガスとしては $\text{a-Si}$ は $\text{SiH}_4$ を主たる成分とするガスを、 $\text{a-Si(n+)}16$ には $\text{SiH}_4$ と $\text{PH}_3$ との混合ガスを使用する。その後、 $\text{a-Si}$ をパターン化してアレイ状にする。プラズマ膜のエッチングには $\text{SF}_6$ ガスによるドライエッチ法を用いる。このとき図4(c)のように端子付近のITOと画素電極のITO膜が露出するように $\text{SiN}$ を除去しておくことが必要である。この上にTFTのドレイン電極を兼ねる信号配線18、ソース電極用の $\text{Cr}/\text{Al-Ta}$  ( $\text{Ta}$ の濃度1.5原子%)をそれぞれ $1000\text{\AA}$ 、 $4000\text{\AA}$ の厚みにスパッタリングにて形成し、パターン化する。この時図4(d)のようになる。その後ドレイン電極をマスクとして $\text{a-Si(n+)}16$ をドライエッチングする。最後に、保護膜として $\text{SiN}$ を $1\mu\text{m}$ 形成し端子部上の $\text{SiN}$ を除去した後、化成バスラインLとゲート端子G1、G2との間を機械的に切断して、TFT基板が完成する(図4(e)参照)。

【0018】図1では各画素が列をなすように配置した場合を示したが、半ピッチずれた配置でも良い。また、付加容量Caddがない場合でも全く同様に製作できることは勿論である。ここではAl材料としてAlにTaを添加した合金を使用した。TiやTaとTiを同時に添加した合金でも良い。この場合添加する量は1.5原子%以下が抵抗やエッチング残渣の点から望ましい。

【0019】次に、対向電極及び青、赤、緑のカラーフィルタアレイを持つ透光性基板と、上記により製造したTFT基板とを厚み $7.3\mu\text{m}$ のスペーサを用いて貼りあわせ、間に液晶を封止し、液晶表示パネルを完成した。以下その構造を簡単に説明する。

【0020】図5にカラー液晶表示パネルの断面全体構造を示す。液晶LCを基準に下部には透明ガラス基板10上にTFT等を形成したTFT基板が配置され、上部にはカラーフィルタFIL、遮光用ブラックマトリクスBM等が形成された透明ガラス基板10bが配置されている。

6

【0021】図5の中央部分は1画素部分の断面を示し、左側は透明ガラス基板10及び10bの左側縁部分で外部引出線の存在する部分の断面を示し、右側は透明ガラス基板及び10bの右側縁部で外部引出線の存在しない部分の断面を示している。図5の左側、右側のそれぞれに示すシール材SLは、液晶LCを封止するように構成されており、液晶封入口(図示していない)を除く透明ガラス基板10及び10bの縁周囲全体に沿って形成されている。シール材SLは、例えば、エポキシ樹脂で形成されている。

【0022】前記上部透明ガラス基板10b側の共通透明画素電極17bは、少なくとも1個所において、銀ペースト材SILによって、下部透明ガラス基板10側に形成された外部引出線17に接続されている。この外部引出線は、前述したゲート電極、ソース電極、ドレイン電極のそれぞれと同一製造工程で形成される。

【0023】配向膜ORI1及びORI2、透明電極17、共通透明画素電極17b、保護膜20及び20b、絶縁膜である $\text{SiN}14$ のそれぞれの層は、シール材SLの内側に形成される。偏光板POL1、POL2は、下部透明ガラス基板10、上部透明ガラス基板10bのそれぞれの外側の表面に形成されている。

【0024】液晶LCは、液晶分子の向きを設定する下部配向膜ORI1及びORI2の間に封入され、シール材SLによってシールされている。

【0025】下部配向膜ORI1は、下部透明ガラス基板10側の保護膜20の上部に形成されている。

【0026】上部透明ガラス基板10bの内側(液晶側)の表面には、遮光膜BM、カラーフィルタFIL、保護膜20b、共通透明画素電極17b及び上部配向膜ORI2が順次積層して設けられている。

【0027】図6に液晶表示装置の一実施例を示す。この装置は、液晶表示パネル81と、該液晶表示パネルに映像信号を与えるための映像信号駆動回路83と、該液晶表示パネルに走査信号を与えるための走査回路84と、該映像信号駆動回路及び走査回路にTFT情報を与えるための制御回路82を有する。制御回路82は電源回路、上位演算処理装置からの情報をTFT情報に変換する回路等を含む。前記実施例で得た液晶表示パネルをそれぞれ用いてこの装置に組み込んだところ、何れも質の高い画像が得られた。

【0028】

【発明の効果】本発明により、TFT基板の製造工程を12%短縮でき、さらに歩留を約5%向上でき、コスト低減を図ることができた。

【図面の簡単な説明】

【図1】本発明の一実施例を示す図。

【図2】従来技術の説明図。

【図3】AlとITOとの接触性を示す図。

【図4】本発明の各部分の詳細を説明するための図。

50

(5)

7

【図5】本発明のTFT基板を用いた液晶表示パネルの実施例を示す図。

【図6】本発明のTFT基板を用いた液晶表示装置の実施例を示す図。


【符号の説明】

10、10b・・・基板、11・・・Cr、12・・・Al-Ta合金材料、13・・・ $\text{Al}_2\text{O}_3$ 、14・・・SiN、15・・・a-Si(i)、16・・・a-Si(n+)、17・・・透明電極、17b・・・共通透明画素電極、18・・・信号配線、18'・・・ソース


8

電極、20、20b・・・保護膜、81・・・液晶表示パネル、82・・・制御回路、83・・・映像信号駆動回路、84・・・走査回路、 $G_1$ 、 $G_2$ ・・・ゲート端子、 $G_1'$ 、 $G_2'$ ・・・ゲート配線、 $D_1$ 、 $D_2$ ・・・ドレイン端子、L・・・化成バスライン、 $l_2$ ・・・切断線、 $l_1$ ・・・化成境界線、Cadd・・・付加容量、PAD・・・化成端子、ORI1、ORI2・・・配向膜、POL1、POL2・・・偏光板、FIL・・・カラーフィルタ、LC・・・液晶、BM・・・ブラックマトリクス、BL・・・バックライト。

【図1】




【図2】




(6)


【図3】



【図4】



【図5】



ORI1, ORI2… 配向膜  
POL1, POL2… 偏光板  
FIL… カラーフィルタ  
17b… 共通透明画素電極

LC… 液晶  
BM… ブラックマトリックス  
BL… バックライト

(7)

【図6】

図 6

